



URTOP MP FB



SINTEC

your waterproofing partner

P.I. Jundiz, C/Arroxeta, P3-4C
01015 – Vitoria (SPAIN)
Tfn: (+34) 945 244 762
Fax: (+34) 945 200 456
info@sintecproof.com
www.sintecproof.com

DESCRIPTION

URTOP MP FB is a synthetic waterproof sheet whose composition is based on a thermoplastic polyolefin (TPO) product of advanced polymerization process, combined with polyester reinforcement and coupled on the back sheet with a 200 gr non-woven polyester mesh. Bitumen resistant. UV resistant. Manufactured under EN 13956 Standards.

USE

URTOP MP FB is suitable for roof waterproofing, mechanical fixation, or a mixed mechanically fixed + fully adhered system, both in new roof, or refurbishment of an existing waterproofing.

PROPERTIES

- Extremely long-lasting.
- Resistant to wind stress.
- Bitumen resistant.
- High tear resistance and tensile strength.
- Excellent puncture resistance, ageing and putrescibility.
- Without protection, high resistance to UV rays.
- Root Resistant according to EN 13948.
- Manufactured without plasticizers, no material migration.
- Environmentally friendly, as contains no chlorides.
- Excellent thermal and dimensional stability.
- High chemical resistance.
- Perfectly weldable with hot air, resulting in a continuous, waterproof surface.

INSTALLATION

- URTOP MP FB waterproofing systems must be installed by experienced and qualified personnel.
- Surfaces must be clean and dry and free from sharp obtrusions, avoiding the installation under high humidity conditions.
- Membrane joins should be made using a hot air welder and should be checked by running a flat headed punch along the whole of the seam.
- Before starting welding adjust the parameters for speed and temperature according to the ambient conditions and the surfaces of the membrane.

PACKAGING AND STORAGE

Colour	Light Grey / Dark Grey
Dimensions	2,10 x 20m
Rolls / pallet	12
Storage	Horizontally and in parallel (never crossed)

Supplied in rolls on cardboard tubing.
Store in the original packaging in a dry and cool place.

URTOP MP FB



URTOP MP FB

CHARACTERISTICS	NORMS	UNITS	VALUES			
Thickness (-5%/+10%)	EN 1849-2	mm	1,2	1,5	1,8	2,0
Weight (-5%/+10%)	EN 1849-2	kg	1,35	1,60	1,88	2,05
Dimensional Stability	EN 1107-2	%	≤ 0,5			
Tensile Strength	EN 12311-2	N/50mm	L, T ≥ 1100			
Elongation	EN 12311-2	%	L, T ≥ 15			
Tear Strength	EN 12310-2	N	L, T ≥ 300			
Foldability at low temperature	EN 495-5	°C	≤ -40			
Joint Peel Strength	EN 12316-2	N/50mm	L,T ≥ 200			
Joint Shear Strength	EN 12317-2	N/50mm	L,T ≥ 600			
Hydrostatic Pressure Resistance, 6h at 0,5 MPa	EN 1928 (B)	-	Waterproof			
Resistance to Static Punching	EN 12730	Kg	≥ 20			
Rection to Fire	EN 13501-1		E			
Impact Resistance	EN 12691 (A)	mm	> 450	> 800	> 900	> 1250
Exposure to UV radiation, elevated temperature and water (5000h)	EN 1297	-	Resistant, grade 0			
Root Resistance	EN 13948	-	No penetration			