



SINTEC

your waterproofing partner

P.I. Jundiz, C/Arroxeta, P3-4C 01015 – Vitoria (SPAIN) Tfn: (+34) 945 244 762 Fax: (+34) 945 200 456 info@sintecproof.com www.sintecproof.com

DESCRIPTION

URTOP MP is a synthetic waterproof sheet whose composition is based on a thermoplastic polyolefin (TPO) product of advanced polymerization process, combined with polyester reinforcement. U.V. resistant. Manufactured under EN 13956 Standards.

USE

URTOP MP is suitable for roof waterproofing, mechanical fixation, both in new roof, or refurbishment of an existing waterproofing.

PROPERTIES

- Extremely long-lasting.
- Resistant to wind stress.
- High tear resistance and tensile strength.
- Excellent puncture resistance, ageing and putrescibility.
- Without protection, high resistance to UV rays.
- Root resistant according to EN 13948.
- Manufactured without plasticizers, no material migration.
- Environmentally friendly, as contains no chlorides.
- Excellent thermal and dimensional stability.
- High chemical resistance.
- Perfectly weldable with hot air, resulting in a continuous, waterproof surface.

INSTALLATION

- URTOP MP waterproofing systems must be installed by experienced and qualified personnel.
- Surfaces must be clean and dry and free from sharp obtrusions, avoiding the installation under high humidity conditions.
- Membrane joins should be made using a hot air welder and should be checked by running
 a flat headed punch along the whole of the seam.
- Before starting welding adjust the parameters for speed and temperature according to the ambient conditions and the surfaces of the membrane.

PACKAGING AND STORAGE

| Colour | Light Grey / Dark Grey |
|----------------|---|
| Dimensions | 2,10 / 1,05 x 20m |
| Rolls / pallet | 23 / 46 / 18 / 36, depending on width and thickness |
| Storage | Horizontally and in parallel (never crossed) |

Supplied in rolls on cardboard tubing.

Store in the original packaging in a dry and cool place.



URTOP MP-

| CHARACTERISTICS | NORMS | UNITS | VALUES | | | |
|--|--------------|--------|--------------------|-------|-------|--------|
| Thickness (-5%/+10%) | EN 1849-2 | mm | 1,2 | 1,5 | 1,8 | 2,0 |
| Weight (-5%/+10%) | EN 1849-2 | kg | 1,15 | 1,40 | 1,68 | 1,85 |
| Dimensional Stability | EN 1107-2 | % | ≤ 0,5 | | | |
| Tensile Strength | EN 12311-2 | N/50mm | L, T≥ 1100 | | | |
| Elongation | EN 12311-2 | % | L, T≥ 15 | | | |
| Tear Strength | EN 12310-2 | Ν | L , T≥ 300 | | | |
| Foldability at low temperature | EN 495-5 | °C | ≤ -40 | | | |
| Joint Peel Strength | EN 12316-2 | N/50mm | L,T ≥ 200 | | | |
| Joint Shear Strength | EN 12317-2 | N/50mm | L,T ≥ 600 | | | |
| Hydrostatic Pressure Resistance, 6h at 0,5 MPa | EN 1928 (B) | - | Waterproof | | | |
| Resistance to Static Punching | EN 12730 | Kg | ≥ 20 | | | |
| Rection to Fire | EN 13501-1 | - | Е | | | |
| Impact Resistance | EN 12691 (A) | mm | ≥ 450 | ≥ 800 | ≥ 900 | ≥ 1250 |
| Exposure to UV radiation, elevated temperature and water (5000h) | EN 1297 | - | Resistant, grade 0 | | | |
| Root Resistance | EN 13948 | - | No penetration | | | |