



**URDIN
SONIC**



SINTEC

your waterproofing partner

P.I. Jundiz, C/Arroxeta, P3-4C
01015 – Vitoria (SPAIN)
Tfn: (+34) 945 244 762
Fax: (+34) 945 200 456
info@sintecproof.com
www.sintecproof.com

DESCRIPTION

URDIN SONIC is a high density polymer-based, asphalt-free, synthetic soundproofing membrane, that offers good acoustic insulation in different building elements.

It is equipped with a tissue non-tissue polypropylene fleece on its upper side to improve the tear strength of the membrane and at the same time offer a protection or a finishing

ADVANTAGES

- High acoustic insulation, combined with soft, flexible elements.
- High sound damping capacity on metal surfaces.
- Flexible.
- Easy to handle and adaptable to uneven surfaces.
- Easy to cut with a knife or scissors
- Good bonding to most of the types of surfaces.
- Acts as a vapour control layer
- Cold- and heat-resistance.
- Excellent ageing resistance.
- Rootproof.

APPLICATION

- Soundproofing against airborne noise in ceilings and lightweight roofs.
- Reduction of impact noise level in all types of floors, sandwiched between floor slabs and loose-laid flooring.
- Damping of impact noise caused by atmospheric agents on metal decks.
- Combined with sound-absorbent materials, it offers products with high acoustic performance.
- Its applications in the industrial field cover from the soundproofing of booths to the acoustic insulation of machine-rooms, gutter pipes, sound-damping of metal sheets, etc.

STANDARD

- Under conformity of EN ISO 140-1, EN ISO 140-3, EN ISO 140-6, EN ISO 140-8, EN ISO 10140 y EN ISO 717/1/2.
- Quality Management System under ISO 9001.

URDIN SONIC



INSTALLATION

SUBSTRATE:

- Lends itself to all types of normal building substrates (renderings, gypsum board, metal, DM, plastic materials). The substrate must be even, smooth, clean and dry. It must also be free from elements that could damage the membrane. If the rendering is old, its condition must be checked to avoid adherence problems of the URDIN SONIC sheet to the rendering

INSTALLATION OF THE MEMBRANE:

- Prior to installing the membrane, an adhesive must be applied to both substrate and membrane, and left to dry according to the instructions of the adhesive manufacturer before bonding the two surfaces. Pressure must be exerted on all the points to ensure correct adherence.
- It could be installed mechanically fastened. The number of fixings will depend on the product, the support and the system where the membrane will be applied.

INSTALLATION OF THE MEMBRANE ON METAL DECKS:

- Extend the roll over the substrate progressively, trying to keep the fleece remained on the upper side so it protects the membrane. The membrane must be applied in such a way that the length of the roll is perpendicular to the direction of the deck profile. The membrane must be made to follow the profile of the metal support at all times, ensuring that there is no formation of air pockets. The thermal insulation boards are then installed, mechanically fastened.

LAPS:

- Overlap 5 cm both vertically and horizontally. Care must be taken to always seal the laps correctly, as small openings can reduce the level of acoustic insulation required.

PRECAUTIONS

- Place the membrane at room temperature > 5°C to avoid a loss of “tacking” of the adhesive.
- Make sure the support is free of moisture before placing the membrane.
- Adhesion tests must be carried out in case the support is not the usual one or has some finishing treatment.
- Make sure that the adhesive is in contact with the entire surface of the support, especially when it is not flat.

PACKAGING AND STORAGE

	URDIN SONIC 50	URDIN SONIC 70	URDIN SONIC 100
Weight (Kg/m ²)	5	7	10
Thickness (mm.)	2.5	3.5	5
Length (m.)	6	5	4
Width (m.)	1.22	1.22	1.2
m ² /roll	7.32	6.10	4.8
Roll / pallet	24	24	21
m ² / pallet	175.68	146.4	100.8

Storage: Horizontal in pallets, without stacking. Product supplied in rolls with carton core inside. Store it into the original packaging, in dry conditions and protected from hot temperatures and UV radiation, not exposed to temperatures higher than 35 °C. The maximum period of storage is 1 year

URDIN SONIC

TECHNICAL PROPERTIES

CARACTERÍSTIQUES	Test method	URDIN SONIC	Unit
Density	-	2.010	Kg/m ³
Tensile strength	NT-67	>30	N/50mm
Elongation	NT-67	> 500	%
Cold flexibility	EN 1109	-20	°C
Tear Strength (nail)	EN 12310-1	153-235	N/50 mm
Fire class	UNE-EN 13501-1	Bs2d0	-
Water vapour resistance factor	UNE-EN 1931 met B	$\mu \geq 1806$	-
Water absorption (24h a 23°C)	ISO 62 met 1	0,03	%
Shore hardness A	NT 74	30 \pm 10	

ACOUSTIC VALUES

CARACTERÍSTIQUES	Test method	Valor	Unit
Young module (E)	-	DM - 1,35637	-
DT - 1,1744	MPa	-	-
Poisson coefficient	-	0,23	-

ACOUSTIC VALUES OF THE INSTALLED PRODUCT

SYSTEM

Metal deck roof made of a corrugate metal sheet of 0.7 mm. support, URDIN SONIC 100 membrane, PIR thermal panel insulation URPIR VV 80, separation layer and a single sheet of synthetic URDIN RP / URTOP

FREQUENCY (Hz)	R with URDIN SONIC	R without URDIN SONIC	Ut
125	23,7	16,4	dB
250	24,2	15,3	dB
500	29,2	23,2	dB
1000	35,4	25	dB
2000	43,4	30,3	dB
4000	54,6	39,7	dB
Global index of weighted acoustic reduction A, RA	33	25	dBA
Global index of acoustic reduction, Rw	34	26	dB

Data according to the test of acoustic air noise insulation under UNE EN ISO 140-3:1995 standard by approved laboratory SRL (UK).

(*) Consult our Acoustic Insulation Systems brochure or contact our Technical Department to know about other systems

